

## Technical Data Sheet

	Standard	Unit	Value
Dimension (LxWxT)	-	mm	1220x185x10,5
Mass per unit	-	Kgs / m <sup>2</sup>	8,37
Packaging (box / pallet)	-	M2	1,806 / 72,24
Level of use Domestic	ISO 10874	Class	23
Level of use Commercial	ISO 10874	Class	33

### General properties - EN 16511

Thickness	ISO 24337	$\Delta t_{avg} \leq 0,50$ mm, relative to nominal value / $t_{max} - t_{min} \leq 0,50$ mm	Complies
Length	ISO 24337	$\leq 1500$ mm: $\Delta l \leq 0,5$ mm / $\geq 1500$ mm: $\Delta l \leq 0,3$ mm/m	Complies
Width	ISO 24337	$\Delta w_{avg} \leq 0,10$ mm, relative to nominal value $w_{max} - w_{min} \leq 0,20$ mm	Complies
Squareness	ISO 24337	$max \leq 0,20$ mm	Complies
Straightness	ISO 24337	$max \leq 0,30$ mm/m	Complies
Openings	ISO 24337	$max \leq 0,20$ mm	Complies
Height difference	ISO 24337	$h_{max} \leq 0,15$ mm	Complies
Flatness of the panel (Length - concave / convex)	ISO 24337	concave $\leq 0,50$ %, / convex $\leq 1,0$ %	Complies
Flatness of the panel (Width - concave / convex)	ISO 24337	concave $\leq 0,15$ %, / convex $\leq 0,20$ %	Complies

### Classification properties - EN 16511

Wear resistance IP	EN 15468, procedure B	$\geq 5000$ cycles	Complies
Impact resistance [mm] (big ball)	EN 13329:2006+A1:2008, Annex F	$\geq 1600$ mm	Complies
Castor chair resistance	EN 425	25 000 cycles	Complies
Resistance to staining	EN 438-2	Groups 1 and 2: grade 5 / Group 3: grade 4	Complies
Residual indentation	EN ISO 24343-1	$\leq 0,2$ mm	Complies
Swelling	ISO 24336	$\leq 18$ %	Complies

### Safety properties - EN 14041

Fire resistance	EN ISO 11925-2 + EN ISO 9239-1: Class EN 13501-1	Class	Bfl-s1
Slip Classification	EN 13893	Class	DS
Formaldehyde emission	EN 717-1	Class	E1
Content pentachlorophenol (PCP)	EN 12673	% mg/kg	Undetectable

### Additional properties

Impact sound reduction	EN ISO 10140	dB ( $\Delta L_w$ )	17
------------------------	--------------	---------------------	----